

Termické odvaděče kondenzátu BK s dvojkovovým regulátorem PN 40 až PN 630

Hranice použitelnosti (DIN 3548, příp. DIN 2401)				
	Materiály		Mezní tlak a teplota	
Typ	DIN	ASTM ¹⁾	PMA/TMA	PMA/TMA
BK 15	C 22.8	A 105	32 bar / 250°C	14,5 bar / 450°C
BK 16	15 Mo 3	A 182 F 1	35 bar / 300°C	28 bar / 450°C
BK 27	15 Mo 3	A 182 F 1	56 bar / 300°C	45 bar / 450°C
BK 28	15 Mo 3	A 182 F 1	87 bar / 300°C	70 bar / 450°C
BK 29	13 CrMo 4 4	A 182 F 12	153 bar / 350°C	35 bar / 550°C
BK 212	10 CrMo 9 10	A 182 F 22	300 bar / 537°C	67 bar / 580°C

